

BRADY B-492 FREEZERBONDZ WHITE POLYESTER THERMAL PRINTABLE LABEL STOCK

TDS No. B-492
Effective Date: 12/11/2018

Description:

GENERAL

Print Technology: Thermal Transfer

Material Type: Polyester

Finish: White film with white thermal transfer printable topcoat

Adhesive: Permanent Acrylic

APPLICATIONS

B-492 Freezerbondz™ markers are designed for use in laboratory identification such as vials, centrifuge tubes, test tubes, straws, and slides.

RECOMMENDED RIBBONS

Brady Series R6400

Brady Series R4300 (alternate)*

Please note that testing described in this Technical Data Sheet was performed on materials printed with the R6400 ribbon.

*Note: R4300 ribbon may be used if chemical resistance is not required with Ethanol, Toluene and Xylene.

SPECIAL FEATURES

B-492 Freezerbondz™ markers can be applied to frozen surfaces including glass and polypropylene stored in liquid nitrogen. B-492 offers excellent print smudge resistance, solvent resistance when using the R6400 Ribbon, and excellent low temperature performance. B-492 performs well in common laboratory environments such as liquid nitrogen and freezer applications.

Select the video links below for demonstration of product use.

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 -Total (excluding liner)	0.0032 inch (0.081 mm)
Adhesion to:	ASTM D 1000	
-Glass	20 minute dwell 24 hour dwell	30 oz/in (33 N/100 mm) 40 oz/in (43 N/100 mm)
-Polypropylene	20 minute dwell 24 hour dwell	12 oz/in (13 N/100 mm) 20 oz/in (22 N/100 mm)
-Stainless steel	20 minute dwell 24 hour dwell	15 oz/inch (16.6 N/100 mm) 22 oz/inch (24.4 N/100 mm)

ENVIRONMENTAL PERFORMANCE PROPERTIES - LABEL APPLIED TO ROOM TEMPERATURE SURFACE

B-492 samples were printed with Series R6400 ribbon. Printed B-492 samples were laminated at room temperature to surfaces listed below and allowed to dwell 24 hours at room temperature prior to exposure to the indicated environments. Labels applied with three applications (gapped, overlapped [with 1/8" overlap], longitudinal to 1.5 mL Eppendorf tubes, 5 mL Cryogenic (polypropylene) vials, 15 mL and 50 mL Polypropylene tubes, 15 mL Glass tubes, wrapped around straws and flat on plastic Whirl-pak bags and boxes. For best results label should be wrapped around and overlapped on itself by at least 1/8".

NOTE for Surfaces: Testing was completed on the following surfaces; Cardboard, Aluminum and Stainless steel boxes¹; Eppendorf 1.5mL tube and tube tops¹, Xryogenic (Polypropylene) vials 5mL², 50mL Polypropylene tubes¹, 15mL Polypropylene tubes³, 15mL Glass tubes¹, Plastic bags (Whirl-pak)⁴ and Straws⁵

Manufacturer:

- 1 = VWR International
 2 = Nalgene®
 3 = Becton Dickinson Labware - Blue Max™ Jr.
 4 = Nasco
 5 = Penetration innovation (Small straw #13441/0280), (Large straw #19042/0010)

ENVIRONMENT	TEST METHOD	TYPICAL RESULTS
High Service Temperature	30 days at elevated temperatures	Moderate discoloration at 230°F (110°C), no visible effect to print. Severe yellowing at 266°F (130°C), label still functional
Liquid Nitrogen	3 cycles of 4 hours at -320°F (-196°C) and 20 hours at room temperature	<ul style="list-style-type: none"> ✓ Glass test tube 1/8" overlap, gapped, longitudinal ✓ Polypropylene tube/vial 1/8" overlap, gapped, longitudinal ✓ Glass microscope slide ✓ Straws; Large & Small ◆ Plastic Whirl-Pak bags ◆ Flat polypropylene ✓ Aluminum foil ✓ Aluminum and cardboard storage boxes
Freezer	3 cycles of 16 hours at -112°F (-80°C) and 8 hours at room temperature	<ul style="list-style-type: none"> ✓ Glass test tube 1/8" overlap, gapped, longitudinal ✓ Polypropylene tube/vial 1/8" overlap, gapped, longitudinal ✓ Glass microscope slide ✓ Straws; Large & Small ◆ Plastic Whirl-Pak bags ✓ Flat polypropylene ✓ Aluminum foil ✓ Stainless steel, aluminum and cardboard storage boxes
Liquid Nitrogen to boiling water	1 hour at -320°F (-190°C) then placed in boiling water 212°F (100°C) for 10 minutes	<ul style="list-style-type: none"> ✓ Glass test tube 1/8" overlap, gapped, longitudinal ✓ Polypropylene tube/vial, gapped ◆ Polypropylene tube/vial, 1/8" overlapped, longitudinal ◆ Glass microscope slide ◆ Flat polypropylene ✓ Aluminum foil
Freezer to boiling water	1 hour at -112°F (-80°C) then placed in boiling water 212°F (100°C) for 10 minutes	<ul style="list-style-type: none"> ✓ Glass test tube 1/8" overlap, gapped, longitudinal ✓ Polypropylene tube/vial, gapped ◆ Polypropylene tube/vial, longitudinal, 1/8" overlap ✓ Glass microscope slide ✓ Flat polypropylene ✓ Aluminum foil

✓ = Label suitable for application; no visible effect, label remains adhered to test surface

◆ = Label may work in application; test results were mixed

✗ = Label not recommended for application; label came off either during testing or after test surface was removed from environment.

¹Metal surfaces should be labeled at room temperature only.

ENVIRONMENTAL PERFORMANCE PROPERTIES - LABEL APPLIED TO COLD SURFACE

B-492 amples were printed with Series R6400 ribbon. Surfaces listed below were stored for 24 hours in either liquid nitrogen at -320°F (-196°C) or in a freezer at -112°F (-80°C). Printed B-492 samples were then laminated immediately after removal of the surfaces from liquid nitrogen or freezer. Labels were applied with three applications (gapped, overlapped [with 1/8" overlap], longitudinal) to glass test tubes (1.1 cm outer diameter) and polypropylene tubes (1.5 ml and 5ml capacity). For best results label should be wrapped around and overlapped on itself by at least 1/8".

ENVIRONMENT	TEST METHOD	TYPICAL RESULTS
Liquid Nitrogen	3 cycles of 4 hours at -320°F (-196°C) and 20 hours at room temperature	<ul style="list-style-type: none"> ✓ Glass test tube, 1/8" overlap ✓ Polypropylene tube/vial, 1/8" overlap ✓ Glass microscope slide ◆ Flat polypropylene ◆ Plastic Whirl-Pak bags ✓ Straws; Large & Small ✓ Aluminum foil ✓ Cardboard storage boxes
Freezer	3 cycles of 16 hours at -112°F (-80°C) and 8 hours at room temperature	<ul style="list-style-type: none"> ✓ Glass test tube, gapped ◆ Glass test tube, longitudinal, 1/8" overlap ✓ Polypropylene tube/vial, gapped ◆ Polypropylene tube/vial, 1/8" overlap, longitudinal ◆ Plastic Whirl-Pak bags ✓ Straws; Large & Small ✓ Glass microscope slide ✓ Flat polypropylene ✓ Aluminum foil ✓ Stainless steel, aluminum and cardboard storage boxes
Liquid Nitrogen to boiling water	1 hour at -320°F (-190°C) then placed in boiling water 212°F (100°C) for 10 minutes	<ul style="list-style-type: none"> ✓ Glass test tube, gapped ◆ Glass test tube 1/8" overlap, longitudinal ✓ Polypropylene tube/vial 1/8" overlap ◆ Glass microscope slide ◆ Flat polypropylene ✓ Aluminum foil
Freezer to boiling water	1 hour at -112°F (-80°C) then placed in boiling water 212°F (100°C) for 10 minutes	<ul style="list-style-type: none"> ✓ Glass test tube, gapped ◆ Glass test tube, 1/8" overlap, longitudinal ✓ Polypropylene tube/vial, 1/8" overlap ✓ Glass microscope slide ✓ Flat polypropylene ✓ Aluminum foil

PERFORMANCE PROPERTIES - CHEMICAL

Flat samples of B-492 were printed with Series R6400 ribbon. Printed samples were laminated and allowed to dwell 24 hours prior to testing. Test conducted at room temperature. Samples immersed in test solvents for 15 minutes. The samples were removed and rubbed 10 times with a cotton swab saturated with the test fluid. The rating scale below show the effect to the quality of the print for each sample.

CHEMICAL REAGENT	R6400 Ribbon EFFECT TO PRINT / TOPCOAT WITH RUB	R6400 Ribbon EFFECT TO PRINT / TOPCOAT WITHOUT RUB	R6400 Ribbon EFFECT TO LABEL STOCK	R4300 Ribbon EFFECT TO PRINT / TOPCOAT WITH RUB	R4300 Ribbon EFFECT TO PRINT / TOPCOAT WITHOUT RUB	R4300 Ribbon EFFECT TO LABEL STOCK
Ethanol	1	1	No visible effect	2	1	Slight print removal
Toluene	1	1	Slight edge infiltration or lifting	4	1	Severe print removal/smear
Isopropanol	1	1	Slight edge infiltration or lifting	2	1	Slight print smear/removal
Xylene	1	1	Slight edge	4	1	Severe print

			infiltration or lifting			smear/removal
Dimethylsulfoxide (DMSO)	1	1	No visible effect	2	1	Slight print smear/removal
50% Acetic Acid	1	1	No visible effect	1	1	No visible effect
10% Sodium Hydroxide	4	4	Topcoat delams from label	4	4	No visible effect
10% Clorox® Bleach Solution	1	1	No visible effect	1	1	No visible effect

Rating Scale Topcoat & Print

- 1 = no visible effect
- 2 = slight smear or print removal, detectable but minimal smear
- 3 = moderate smear or print removal (print still legible)
- 4 = severe smear or print removal (print illegible or just barely legible)
- 5 = complete print and/or topcoat removal

Rating Scale - Adhesive

- 1 = no visible effect
- 2 = slight effect, slight edge infiltration or lifting
- 3 = moderate effect, severe edge infiltration or lifting
- 4 = severe effect, severe edge infiltration
- 5 = label removed

Shelf Life:

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

Trademarks:

ASTM: American Society for Testing and Materials (U.S.A.)
 All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units.
 BradyPrinter™ is a trademark of Brady Worldwide, Inc.
 Clorox® is a registered trademark of Brady Worldwide, Inc.
 Freezerbondz™ is a trademark of Brady Worldwide, Inc.
 Nalgene® is a registered trademark of Nalge Nunc International Corporation
 S.I.: International System of Units

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2018 Brady Worldwide, Inc. | All Rights Reserved
 Material may not be reproduced or distributed in any form without written permission.